



APPLICATION NOTE - SR003

General Application Guidelines

Silent Running may be brushed, rolled or sprayed on. Ultimate goal is to get 40 - 50 mils total thickness in multiple coats.

The thicker the substrate the more coats of Silent Running will be required.

Wait until the applied coat is dry to the touch and then apply the next coat.

Temperature and humidity will affect dry times. At 70 degrees F and average humidity, Silent Running will dry to the touch in about 1 hour.

Do not thin regardless of application method.

Brushing - use a wide (4"), thick nylon bristle brush. Do not tip off on edge of can, keep a lot of material on the brush. Use short strokes, apply thick. You should be able to apply 10-12 mils per coat. Try not to "paint" back and forth as this will just cause the coat to become thinner and thinner.

Roller - use a short knap (3/8") cloth roller. Use short strokes, try to avoid rolling back and forth and this will also cause the coat to become thinner. Use a light brush to "tip off" the stipples if desired.

Spray - We use a pressure pot with a Binks 2001 spray gun and a large orifice tip (air nozzle is 66SD and fluid nozzle is 66SS, or specify a gel coat tip). About 60 lbs. of pressure at the pot and 30-40 lbs. at the gun. Hold the tip about 14" from the surface. You should be able to spray 15-18 mils per coat.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.
30 Tyler Street
PO Box 120183
East Haven, CT 06512

Current Composites Coatings
Phone: 203-469-1337
Toll free: 877-436-6542
Fax: 203-467-8435