



APPLICATION NOTE - SR004

Finishing

To get the best surface finish, spray application of Silent Running works the best.

Silent Running can very easily be sprayed at a thickness of 15-18 mils per coat.

If rolling Silent Running on, follow up with a fine bristle or foam brush to lightly tip off the stippling left behind by the roller.

If brushing on, again, very lightly go over the surface to smooth out the brush marks. Be careful as too much brushing will thin the surface coating reducing the amount applied.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.
30 Tyler Street
PO Box 120183
East Haven, CT 06512

Current Composites Coatings
Phone: 203-469-1337
Toll free: 877-436-6542
Fax: 203-467-8435