



APPLICATION NOTE - SR006

Warm Weather Application

Silent Running is best applied with the ambient, material and substrate temperature in the range of 65 - 85 degrees F.

Higher temperatures will result in longer dry times, and Silent Running should be applied in thinner coats as sagging may occur.

Higher temperature coats should not exceed 12 - 15 mils in thickness, if there is any question, a small test area should be coated. Wait 20-30 minutes to observe the results.

Remember, usually with higher temperatures comes higher humidity. Higher humidity will result in longer dry times.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.
30 Tyler Street
PO Box 120183
East Haven, CT 06512

Current Composites Coatings
Phone: 203-469-1337
Toll free: 877-436-6542
Fax: 203-467-8435